Emerging materials in neuromorphic computing: Guest editorial

Cite as: APL Mater. 8, 010401 (2020); https://doi.org/10.1063/1.5143659 Submitted: 26 December 2019 . Accepted: 29 December 2019 . Published Online: 17 January 2020

Geoffrey W. Burr 🗓, Abu Sebastian 🗓, Elisa Vianello 🗓, Rainer Waser 🗓, and Stuart Parkin 🗓

COLLECTIONS

Paper published as part of the special topic on Emerging Materials in Neuromorphic Computing








ARTICLES YOU MAY BE INTERESTED IN

Ferroelectric materials for neuromorphic computing APL Materials 7, 091109 (2019); https://doi.org/10.1063/1.5108562

A comprehensive review on emerging artificial neuromorphic devices
Applied Physics Reviews 7, 011312 (2020); https://doi.org/10.1063/1.5118217

Perspective: A review on memristive hardware for neuromorphic computation Journal of Applied Physics 124, 151903 (2018); https://doi.org/10.1063/1.5037835





EDITORIAL APL Materials scitation.org/journal/apm

Emerging materials in neuromorphic computing: Guest editorial

Cite as: APL Mater. 8, 010401 (2020); doi: 10.1063/1.5143659 Submitted: 26 December 2019 • Accepted: 29 December 2019 • Published Online: 17 January 2020















Geoffrey W. Burr, 1.a) D Abu Sebastian, 2.b) Elisa Vianello, 3.c) Rainer Waser, 4.d,e) D and Stuart Parkin 5.f,9) D



AFFILIATIONS

- ¹IBM Research–Almaden, San Jose, California 95120, USA
- ²IBM Research–Zurich, Rüschlikon, Switzerland
- 3CEA-Leti, Grenoble, France
- ⁴RWTH Aachen University, Aachen, Germany
- ⁵Max Planck Institute of Microstructure Physics, Halle, Germany

Note: This paper is part of the Special Topic on Emerging Materials in Neuromorphic Computing.

- a) Author to whom correspondence should be addressed: gwburr@us.ibm.com
- b) Electronic mail: ase@zurich.ibm.com
- c) Electronic mail: elisa.vianello@cea.fr
- d) Electronic mail: waser@iwe.rwth-aachen.de
- Also at: Peter Grünberg Institute, Jülich Research Center, Jülich, Germany.
- ^{f)}Electronic mail: stuart.parkin@mpi-halle.mpg.de
- Also at: Institute of Physics, Martin-Luther-University Halle-Wittenberg, Halle, Germany.

https://doi.org/10.1063/1.5143659

I. INTRODUCTION

For more than five decades, the flexibility of the von Neumann architecture—in which data from discrete memory units arrive at dedicated compute units as both operations and operands—has driven exponential improvements in system performance. These computing systems require large amounts of data to be shuttled back and forth at high speeds during the execution of computational tasks. However, as device scaling has slowed due to power and voltage considerations, the time and energy spent transporting data across the so-called "von Neumann bottleneck" between memory and compute units have become problematic. These performance bottlenecks and significant area/power inefficiencies are particularly inescapable for data-centric applications, such as real-time image recognition and natural language processing, where the state-of-theart von Neumann systems work hard to match the performance of an average human.

We are on the cusp of a revolution in artificial intelligence (AI) and cognitive computing, with algorithmic advances that have allowed Deep Neural Networks (DNNs) to approach or even surpass the performance of humans on many tasks such as pattern-recognition, game-playing, machine translation, and more.

However, the computers that run today's AI algorithms are based on the von Neumann architecture, which means that these machines are many orders of magnitude less energy-efficient than the human brain even as they pass the brain in speed or approach it in accuracy. Thus, it is becoming increasingly clear that, to build efficient cognitive computers, we need to transition to novel architectures where memory and processing are better collocated.1

The human brain suggests an intriguing non-von Neumann computing paradigm for future computing systems, referred to as either brain-inspired or neuromorphic computing. The brain is characterized by its massively parallel architecture connecting myriad low-power computing elements (neurons) and adaptive memory elements (synapses). It is natural to look to the human brain for inspiration since it is a remarkable engine of cognition that performs computations on the order of peta-ops per joule. Since the brain can outperform modern processors on many tasks involving unstructured data classification and pattern recognition, it provides an "existence proof" for an ultralow power cognitive

Unfortunately, we are still quite far from attaining a comprehensive understanding of how the brain computes. However, APL Materials EDITORIAL scitation.org/journal/apm

we have uncovered certain salient features of this computing system such as the collocation of memory and processing, a computing fabric comprising large-scale networks of neurons and plastic synapses, and spike-based communication and processing of information. Early studies of the brain led to the creation of artificial neural networks. These evolved over many decades into the DNNs responsible for the current AI revolution behind recent breakthroughs in image classification, speech recognition, machine translation, customer prediction, fraud detection, game-playing, and many other commercially relevant applications. Based on these insights, researchers have begun to envision neuromorphic computing systems at multiple levels of inspiration or abstraction.

In the brain, memory and processing are highly entwined. Hence, the memory unit can be expected to play a key role in brain-inspired computing systems. The scaling of dense non-volatile memory (NVM) crossbar arrays to few-nanometer critical dimensions has been recognized as one path to build computing systems that can mimic the massive parallelism and low-power operation found in the human brain. The human brain has a high degree of connectivity, with any given neuron having as many as 10 000 inputs from other neurons. Dense arrays of NVM elements provide an opportunity to emulate this connectivity in hardware if various engineering difficulties can be overcome. In particular, very high-density, low-power, variable-state, programmable, and nonvolatile memory devices could play a central role.

II. SPECIAL ISSUE

In this context of neuromorphic computing as a promising area of research for future, energy-efficient computing systems, we organized the present Special Issue in *APL Materials* entitled "Emerging Materials in Neuromorphic Computing."

This special issue provides a comprehensive overview on emerging materials at the active frontier of neuromorphic computing. We considered new materials and new uses for established materials, within the context of brain-inspired computing algorithms, ranging from spiking networks to oscillator networks to reservoir computing to deep neural networks. We sought out the interdisciplinary perspective which could integrate materials science, physics, chemistry, computer science, and engineering. The selected articles give a state-of-the-art overview of the progress over the past few years in this topic area.

Many of these articles address resistive switching materials for neuromorphic computing, including devices based on

- phase-change memory, 3,4
- memristive oxide-filament resistive devices, 5-9
- electrochemical metal-filament devices, ^{10,11}
- ferroelectric¹² and organic ferroelectric devices,¹³
- nonfilamentary RRAM materials, 14-16 and
- topological insulator materials.

Several papers studied the interplay between memristor device characteristics and neuromorphic applications. ^{8,18,19} Other papers focused on photonic applications relevant to neuromorphic computing. ^{3,9,20,21} Finally, several papers addressed the stochastic

operation of devices for the novel synaptic and/or neuronal behavior^{6,11,14} to enable stochastic learning algorithms.

ACKNOWLEDGMENTS

We hope this Special Topic will be relevant and interesting for researchers both in and outside the field.

We would like to acknowledge all authors who contributed to this Special Topic, as well as Editors Professor Judith L. MacManus-Driscoll and Diana Schlamadinger, Editorial Assistant Jacquelyn O. Cagna, and Assistant Journal Manager Emma N. Van Burns.

REFERENCES

- ¹G. W. Burr, R. M. Shelby, A. Sebastian, S. Kim, S. Kim, S. Sidler, K. Virwani, M. Ishii, P. Narayanan, A. Fumarola, L. L. Sanches, I. Boybat, M. L. Gallo, K. Moon, J. Woo, H. Hwang, and Y. Leblebici, "Neuromorphic computing using non-volatile memory," Adv. Phys.: X 2, 89–124 (2017).
- ²A. Sebastian, M. Le Gallo, G. W. Burr, S. Kim, M. BrightSky, and E. Eleftheriou, "Tutorial: Brain-inspired computing using phase-change memory devices," J. Appl. Phys. 124, 111101 (2018).
- ³S. G.-C. Carrillo, E. Gemo, X. Li, N. Youngblood, A. Katumba, P. Bienstman, W. Pernice, H. Bhaskaran, and C. D. Wright, "Behavioral modeling of integrated phase-change photonic devices for neuromorphic computing applications," APL Mater. 7, 091113 (2019).
- ⁴T.-T. Jiang, J.-J. Wang, L. Lu, C.-S. Ma, D.-L. Zhang, F. Rao, C.-L. Jia, and W. Zhang, "Progressive amorphization of GeSbTe phase-change material under electron beam irradiation," APL Mater. 7, 081121 (2019).
- ⁵F. Cüppers, S. Menzel, C. Bengel, A. Hardtdegen, M. von Witzleben, U. Böttger, R. Waser, and S. Hoffmann-Eifert, "Exploiting the switching dynamics of HfO₂-based ReRAM devices for reliable analog memristive behavior," APL Mater. 7, 091105 (2019).
- ⁶T. Dalgaty, M. Payvand, F. Moro, D. R. B. Ly, F. Pebay-Peyroula, J. Casas, G. Indiveri, and E. Vianello, "Hybrid neuromorphic circuits exploiting non-conventional properties of RRAM for massively parallel local plasticity mechanisms," APL Mater. 7, 081125 (2019).
- ⁷V. Milo, C. Zambelli, P. Olivo, E. Pérez, M. K. Mahadevaiah, O. G. Ossorio, C. Wenger, and D. Ielmini, "Multilevel HfO₂-based RRAM devices for low-power neuromorphic networks," APL Mater. 7, 081120 (2019).
- ⁸P. Huang, Z. Zhou, Y. Zhang, Y. Xiang, R. Han, L. Liu, X. Liu, and J. Kang, "Hardware implementation of RRAM based binarized neural networks," APL Mater. 7, 081105 (2019).
- ⁹F. M. Simanjuntak, S. Chandrasekaran, C.-C. Lin, and T.-Y. Tseng, "ZnO₂/ZnO bilayer switching film for making fully transparent analog memristor devices," APL Mater. 7, 051108 (2019).
- ¹⁰P. Pragnya, A. Pinkowitz, R. Hull, and D. Gall, "Electrochemical memristive devices based on submonolayer metal deposition," APL Mater. 7, 101121 (2019).
- ¹¹B. Dang, K. Liu, J. Zhu, L. Xu, T. Zhang, C. Cheng, H. Wang, Y. Yang, Y. Hao, and R. Huang, "Stochastic neuron based on IGZO Schottky diodes for neuromorphic computing," APL Mater. 7, 071114 (2019).
- ¹²S. Oh, H. Hwang, and I. K. Yoo, "Ferroelectric materials for neuromorphic computing," APL Mater. 7, 091109 (2019).
- ¹³S. Majumdar, H. Tan, I. Pande, and S. van Dijken, "Crossover from synaptic to neuronal functionalities through carrier concentration control in Nb-doped SrTiO₃-based organic ferroelectric tunnel junctions," APL Mater. 7, 091114 (2019).
- 14 D. Khilwani, V. Moghe, S. Lashkare, V. Saraswat, P. Kumbhare, M. Shojaei Baghini, S. Jandhyala, S. Subramoney, and U. Ganguly, " $Pr_xCa_{1-x}MnO_3$ based stochastic neuron for Boltzmann machine to solve "maximum cut" problem," APL Mater. 7, 091112 (2019).

APL Materials EDITORIAL scitation.org/journal/apm

- ¹⁵H. J. Kim, M. Kim, K. Beom, H. Lee, C. J. Kang, and T.-S. Yoon, "A Pt/ITO/CeO₂/Pt memristor with an analog, linear, symmetric, and long-term stable synaptic weight modulation," APL Mater. 7, 071113 (2019).
- ¹⁶S. A. Howard, C. N. Singh, G. J. Paez, M. J. Wahila, L. W. Wangoh, S. Sallis, K. Tirpak, Y. Liang, D. Prendergast, M. Zuba, J. Rana, A. Weidenbach, T. M. McCrone, W. Yang, T.-L. Lee, F. Rodolakis, W. Doolittle, W.-C. Lee, and L. F. J. Piper, "Direct observation of delithiation as the origin of analog memristance in Li_xNbO₂," APL Mater. 7, 071103 (2019).
- ¹⁷Q. Wan, P. Zhang, Q. Shao, M. T. Sharbati, J. R. Erickson, K. L. Wang, and F. Xiong, "(Bi_{0.2}Sb_{0.8})₂Te₃ based dynamic synapses with programmable spatiotemporal dynamics," APL Mater. 7, 101107 (2019).
- ¹⁸A. Siemon, S. Ferch, A. Heittmann, R. Waser, D. J. Wouters, and S. Menzel, "Analyses of a 1-layer neuromorphic network using memristive devices with noncontinuous resistance levels," APL Mater. 7, 091110 (2019).
- ¹⁹A. Yanguas-Gil, "Memristor design rules for dynamic learning and edge processing applications," APL Mater. 7, 091102 (2019).
- ²⁰ R. Amin, J. K. George, S. Sun, T. Ferreira de Lima, A. N. Tait, J. B. Khurgin, M. Miscuglio, B. J. Shastri, P. R. Prucnal, T. El-Ghazawi, and V. J. Sorger, "ITO-based electro-absorption modulator for photonic neural activation function," APL Mater. 7, 081112 (2019).
- ²¹ M. Miscuglio, G. C. Adam, D. Kuzum, and V. J. Sorger, "Roadmap on material-function mapping for photonic-electronic hybrid neural networks," APL Mater. 7, 100903 (2019).